

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188	
Public Reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comment regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave Blank)		2. REPORT DATE 22 January 2002		3. REPORT TYPE AND DATES COVERED Final Technical; 1 Jun 1995 - 31 May 2001
4. TITLE AND SUBTITLE Developing Innovative Mesoscale Actuator Devices for Use in Rotorcraft Systems			5. FUNDING NUMBERS G:DAAH04-95-1-0095, P00003	
6. AUTHOR(S) G.P. Carman, B.S. Dunn, P.P. Friedmann, H.T. Hahn C.-M. Ho, C.-J. Kim				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of California, Los Angeles, School of Engineering & Applied Science 38-137 Engineering IV, Box 951597 Los Angeles, CA 90095-1597			8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U. S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSORING / MONITORING AGENCY REPORT NUMBER DAAH04-95-1-0095 33894.27-MS-MUR	
11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.				
12 a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.			12 b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) The primary goal of this MURI was to develop a superior meso-scale piezoelectric actuator device when compared to conventional smart actuation systems. The secondary goal was to evaluate the potential use of the device in rotorcraft systems to alter fluid-structure interactions and to decrease vibration loads and/or alleviate dynamic stall. The piezoelectric activated device utilized frequency rectification concepts along with single crystal silicon micro-machined gears to produce step-like motions amplifying the displacement output of conventional piezoelectric stacks from microns to millimeters. The order of magnitude displacement improvement was also reflected in an order of magnitude increased power output of the system when operated in structural systems such as the rotorcraft. Accomplishing this goal required several fundamental science and engineering questions to be addressed. These included but were not limited to the long term electro-mechanical fatigue of piezoelectrics, the intrinsic strength of single crystal MEMS components, meso-scale manufacturing concepts, and development of thin film lithium batteries. In regards to rotorcraft applications, experimental and analytical studies indicated substantial reductions in vibrations up to 90% along with alleviation of dynamic stall.				
14. SUBJECT TERMS piezoelectric, rotorcraft, active flow control, active control flap, inchworm motor, mesoscale actuator, MEMS, fatigue, strength, battery			15. NUMBER OF PAGES 17	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OR REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION ON THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

NSN 7540-01-280-5500

Standard Form 298 (Rev.2-89)
Prescribed by ANSI Std. Z392

298-102

20030605 189

I. Abstract

The primary goal of this MURI was to develop a superior meso-scale piezoelectric actuator device when compared to conventional smart actuation systems. The secondary goals was to evaluate the potential use of the device in rotorcraft systems to alter fluid-structure interactions and to decrease vibration loads and/or alleviate dynamic stall. The piezoelectric activated device utilized frequency rectification concepts along with single crystal silicon micro-machined gears to produce step-like motions amplifying the displacement output of conventional piezoelectric stacks from microns to millimeters. The order of magnitude displacement improvement was also reflected in an order of magnitude increased power output of the system when operated in structural systems such as the rotorcraft. Accomplishing this goal required several fundamental science and engineering questions to be addressed. These included but were not limited to the long term electro-mechanical fatigue of piezoelectrics, the intrinsic strength of single crystal MEMS components, meso-scale manufacturing concepts, and development of thin film lithium batteries. In regards to rotorcraft applications, experimental and analytical studies indicated substantial reductions in vibrations up to 90% along with alleviation of dynamic stall.

II. Statement of Problem Studied

Prior to this program, piezoelectrics were limited in displacement output, typically on the order of microns. Previous attempts to remedy this problem included displacement amplification techniques that led to corresponding reduction in force outputs. While successful, these approaches do not improve the overall power density of the piezoelectric actuator thereby limiting its usefulness. During this MURI program we proposed and implemented a frequency rectification approach to increase the displacements by reducing frequency output rather than force output. Since piezoelectrics operate in the kHz regime and the structural community requires operation in the 1-100 Hz regime frequency rectification is both acceptable and desirable. Therefore, rectifying the frequency from 1000 Hz to 100 Hz will increase the power output of a piezoelectric actuator by one order of magnitude. Based on the research findings made during this program on this concept, DARPA initiated a Compact Hybrid Actuator Program to design, fabricate, and test various frequency rectification devices. A device similar to the one developed under this MURI is now being commercialized by Burleigh Instruments, the original developer of piezoelectric inchworm motors.

Developing a successful piezoelectric frequency rectification device required collaboration between material scientists, mechanical engineers, and designers. Fabrication of small gearing mechanisms, on the order of microns, transferred macroscopic mechanical load in the device. Both developing manufacturing approaches and assessing strength of these microcomponents was a challenging task with relatively little research available in the open literature. In addition to fabricating small components, the operation of the piezoelectric ceramic at high fields and large stresses over millions of cycles is not understood. Finally, integrating micro-based components into a macro/meso-structure poses significant manufacturing challenges to operating a frequency rectification device.

The frequency rectification device developed under this program was called the meso-scale actuator device (MAD). We investigated applications to three specific rotorcraft problems, vibration reduction, blade vortex interaction, and dynamic stall. Both the vibration reduction problem and blade vortex interaction problem were studied analytically using an active flap on the blades of the rotorcraft. Potentially, the MAD device could control these active control flaps. To investigate dynamic stall, we experimentally investigated flow control concepts near the leading edge of the rotorblade. During this study, we discovered that up to 90% of the vibrations can be reduced with the active control flap and dynamic stall can be significantly delayed using flow control concepts.

In general, this program developed a piezoelectric frequency rectification device (MAD) that integrated micro-machined components and piezoelectrics into a device far superior to its individual components. The palm size device (characteristic dimension on the order of 100mm) could produce up to 100 lb output force with motion speeds up to 10 mm/s. These properties represent an order of magnitude improvement over existing piezoelectric stack actuation systems and relies on the frequency rectification concept. The palm-size device was investigated for potential use in rotorcraft systems with significant reductions in vibrations or alleviation of dynamic stall reported. During this project a number of scientific advancements were made that are not detailed in this report. For detailed information on each research area, the reader is referred to the more complete descriptions provided in the published papers listed in section IV.


III. Summary of Important Results

Meso-Scale Actuator Device (MAD):

1. Demonstrated that MEMS microridges fabricated on separate wafers could be engaged and disengaged using a piezoelectric drive actuator. This work established that MEMS components combined with active materials (piezoelectric) provide new approaches for developing actuation systems with characteristics far superior to conventional ones.
2. Demonstrated that MEMS microridges combined with a piezoelectric stack can be used to produce a step-like motion (i.e., frequency rectification) increasing the overall displacement output from microns to millimeters, an order of magnitude larger than the stand alone stack. This work confirms that tolerances associated with microscopic components, while challenging, does not represent a fundamental obstacle for producing hybrid actuator systems.
3. Experimentally synchronized the mechanical interlocking of microcomponents at frequencies on the order of one kilohertz. For the helicopter application, which is the focus of this research, the power produced by the MAD system operated at one kilohertz was one order of magnitude larger than conventional piezoelectric stacks.
4. Demonstrated that microcomponents can transfer macroscopic loads, a first for the scientific community. A silicon chip containing ridges on the order of 5 microns supported mechanical loads well over 200 N. This fundamental work opened the door to new applications for microcomponents that one day may replace conventional gearing mechanisms in everything from mechanical watches to automobiles. However, these results also indicate that a large

void exists in available scientific data regarding the strength/fatigue of microcomponents. Our experimental results support this contention and also suggest geometry, material, and manufacturing processes play a prominent role in dictating the overall strength.

5. Designed/fabricated and tested a prototype meso-scale actuator device (MAD) supporting 500 N load moving at 10 mm/s (i.e. 1000 Hz) with displacements approaching a millimeter (see Figure 1). Therefore, the new actuator represents a remarkable improvement over existing systems. While the results were very promising, we would like to note that damage to the ridges during walking and the constraint of the step size are limiting features of the device. If the ridges could be fabricated from tougher materials (we also examined other materials) and the step size could be variable the device would be ideal for many structural applications including those that require precision control.



Strength of Micro-Components:

1. Designed new tests to characterize strength/fatigue of microcomponents. This effort included designing and fabricating an innovative micro-scale dog-bone specimen similar to ASTM standards required for evaluating macroscopic material systems. In regards to the micro-scale dog-bone specimens, several different materials manufactured with different processes were evaluated. Initial results indicate that manufacturing processes prominently influence the strength (i.e. over 100%) of a microcomponent.
2. Measuring the strain response of the micro-structures is difficult. To overcome this problem, a laser interferometric system was constructed to monitor surface deflections on the specimen. The system provides submicron resolution at loading frequencies that approach 100 Hz. Currently this system is being used to measure surface strains during tensile loading.

Piezoelectric Materials:

1. Piezoelectric materials are the most plausible candidates for use in the meso-scale actuator device. However, the actuator will be operated at large frequencies (i.e. kHz) for long periods with a total life approaching 5000 hours (rotorcraft requirement). The long term cycling of piezoelectric materials under combined mechanical and electrical loading has

never been studied by the scientific community and thus poses a serious obstacle to the smart materials community. While a few researchers have investigated electric fatigue, they did not study electro-mechanical fatigue. We have found that electro-mechanical fatigue is a truly complicated problem. Our work indicates that actuator piezoceramics, those producing over 2000 (some over 4000) microstrain, fatigue fundamentally different than pure electric fatigue and to a large extent depend upon the material being studied. In the severe nonlinear regime, generally the degradation can be mitigated with the application of compressive mechanical loads and exacerbated with the application of tensile loads. In the quasi-linear regime, the interaction between stresses caused by internal variant electric fields and external mechanical loads is not fully understood at this time, due to the fact that domain reorientation effects are dependent upon both load and electric field levels.

2. Analytically demonstrated that "optimal" piezoelectric properties exist to eliminate stress concentrations around internal anomalies within the material. These optimal properties, which are independent of anomaly geometry and distribution, suggest a universally valid relationship. Recognizing these relationships will pave the way for developing new piezoelectric materials, we proposed a new approach not previously considered by the scientific community to eliminate fatigue, i.e. tailoring the coefficients without reducing the strain output. This finding represents a scientific discovery that has significant ramifications for future piezoelectric materials such as the new single crystal piezoelectrics.
3. Evaluated internal strain distributions during domain evolution with a laser interferometric technique to understand the fatigue process. This study was the first that used Moire Interferometry, a full field strain measurement technique, to measure the distribution of strains between dissimilar domain structures. Results indicate that dissimilar domains produce considerably larger internal strain/stresses than previously thought. These results have significant implications regarding the long-term fatigue of new single crystal piezoelectric materials, which undergo a phase change, producing two dissimilar structures within the material. Our results indicate that these two structures are a key factor that causes fatigue degradation of this class of ferroelectric materials. By understanding this phenomenon, we believe that it can be overcome. One approach being investigated is applying external mechanical loads to mitigate the internal stress concentrations and/or adjusting material properties (see 2 above).
4. Developed a nonlinear finite element code to understand the internal stress distribution in piezoelectric ceramics undergoing phase transformations, including domain wall motion. While a handful of these nonlinear models are currently being developed, the UCLA model is the only one (we are aware of) that has been validated with experimental results generated from full field measurements, i.e. the Moire system. Current results are truly promising; however, they also indicate that modeling the nonlinear behavior of piezoelectric actuators is still in its infancy. Once again these models represent a critical component in understanding the response of current and proposed piezoelectric actuators.
5. Initiated a collaborative study with Rockwell Science Center to investigate some novel piezoelectric materials including PLZT and new single crystal piezoelectric materials. Test results on the Rockwell PLZT composition revealed a behavior not previously observed with other piezoelectric materials. When a compressive stress is applied to this material, instead of the typical displacement degradation, the PLZT materials response improved. We suggest that this improvement is the result of domain wall motion initiated by the compressive stress that is subsequently reactivated when the electric field is applied, thereby amplifying the

with a decrease in cell capacity.

Blade Manufacturing:

1. Designed and fabricated a Wortmann FX-098 composite blade for wind tunnel testing. In addition to this blade several other geometries were manufactured using Laminated Object Manufacturing to permit quick and easy verification of actuator/sensor positioning within a typical blade design. The span-wise uniformity, a critical requirement, measured by an X-Y-Z measurement probe station was found to be very consistent. Without this component of research in the program it would be difficult to conduct a collaborative study on issues ranging from actuator development to rotorcraft applications. The blade provided the opportunity to quickly evaluate and test both the research concepts and actuator designs. In one sense, this portion of the program provides the vehicle for conducting collaborative studies amongst the various researchers.

Experimental Dynamic Stall Alleviation:

1. Using the blade system manufactured, experimental tests were conducted to understand the stall phenomena associated with rotorcraft systems in an effort to delay these detrimental phenomena. We implemented several different techniques to alleviate separation effects that lead to wing structure stall. This research has demonstrated that small displacement have beneficial influences on blades operated in the stall regime including dynamic stall.
2. Measured static pressure via 26 pressure sensors integrated into the Wortmann FX-098 wing structure. This data is a critical component to understand and control the separation effects causing the wing structure to stall. The pressure sensors provided less than 5% differences when compared to a validated load cell calculated over the entire angle-of-attack (AOA) operating range.
3. Validated static and unsteady stall characteristics for both the Wortmann FX-098 wing and a previously studied Wortmann FX-137 wing. For the static stall cases, we demonstrated that a small disturbance placed at or near the leading edge could delay stall and eliminate the associated hysteresis. This result suggested that similar results might be possible for the dynamic stall case. In fact recent tests have confirmed that dynamic stall can be alleviated with small surface displacements.
4. The ability to control the dynamic stall problem represented a fundamental scientific issue addressed during this program. Recently, we measured the transient pressure distribution for dynamic stall conditions to gain a better understanding of this phenomenon. Very little, in terms of control work using small structural perturbations, is being done in this area. Successful control techniques that manipulate the unsteady flow characteristics could lead to more general applications of the concepts proposed in this research and possibly real-time control of a rotor-blade.
5. Developing a miniature device that can adjust to the large range of operating conditions encountered in a rotor-blade is also being investigated. The ability of the device to produce substantial reduction of dynamic stall effects is the overall objective of this portion of the research. Here, the existence, strength, growth and convection of the dynamic stall vortex (d-s-v) are of primary importance. Currently, the qualitative features of the d-s-v are present but

displacements capabilities of the actuator. This result is consistent with the domain wall management philosophy that we are implementing to produce piezoelectric materials whose strain output exceeds 4000 microstrain. The principal problem with these large displacement actuators is still fatigue degradation during long term cyclic loading.

6. Evaluated several piezoelectric stacks for increasing the strain output using domain wall concepts. Results indicated that the strain output could be doubled and in some circumstance tripled for appropriate loading conditions. The stacks produces strains on the order of 3500 microstrain compared with manufacturers measured 1000 microstrains. Fatigue tests suggest that the increased domain wall motion leads to quicker degradation than found on stacks operated at "acceptable drive and load levels." This work has guided Boeing rotorcraft to operate the stacks for an upcoming flight test on a rotorcraft incorporating piezoelectric stacks.

Polymer Lithium Battery:

1. Used lithium polymer batteries to power piezoelectric actuators. This work demonstrated that thin film lithium batteries are able to supply ac power for operating multi-layer actuators. Some of the key features of this work are as follows:
 - Lithium polymer batteries were operated in ac mode as compared to standard dc operation. Such ac operation is essential for actuator applications.
 - 6 and 12 Volt battery modules were constructed which operated up to 1000 Hz and exhibited energy densities of 150 to 200 mAh/g
 - The battery modules demonstrated the powering of various piezoelectric stack actuators. A lithium polymer battery was also used to power a piezoelectric actuator patch that was part of a damage detection system.
 - The battery modules are rechargeable and, operating at 100 Hz, as many as 100 discharge/charge cycles were demonstrated
 - A study of cycling behavior showed that loss of battery capacity is a function of frequency over the range 10 to 500 Hz.
2. Developed and characterized battery materials. This work primarily involved studies of the cathode material. The emphasis was on determining how the fundamental properties of the cathode were affected by battery processing and operational conditions.
 - For the cathode material, we selected vanadium oxide aerogels, optimized the processing conditions and developed methods for integrating this material into the battery structure. The material has a reversible lithium capacity in excess of 400 mAh/g, which is three times greater than commercial cathode materials.
 - *In-situ* electrochemical impedance measurements and simulations conclusively showed that the formation of a surface layer leads to an increase in charge transfer resistance at the cathode/electrolyte interface and subsequent capacity loss in the battery.
 - Processing conditions which rigorously avoid moisture exposure were shown to be the key feature in minimizing/avoiding the formation of deleterious surface layers and leading to excellent capacity on cycling.
 - Atomic force microscopy (AFM) was combined with electrochemical characterization methods to observe, in real-time, morphological changes in the cathode during cell discharge/charge. Overdischarge is found to cause irreversible changes in cathode thickness which correlates

some quantitative aspects of the vortex have not yet been validated and will be researched during the final two years.

Rotorcraft Vibration Alleviation Analysis:

1. Developed an unsteady aerodynamic model of airfoil/flap combination modeled using rational function approximation (RFA), which includes compressibility and unsteady free stream effects
2. Combined the unsteady aerodynamic model, with a free wake and a finite element model of the blade structural dynamics, to produce an aeroelastic code simulating vibration reduction in forward flight. This code produced better agreement with experimental data obtained Fulton & Ormiston (AHS Proceedings 1998, pp. 433-451) than any other code available.
4. Demonstrated that vibration reduction due to high-speed forward flight (VRHFF) and vibration alleviation due to BVI (VABVI) represent two fundamentally different problems. In both cases the actively controlled flap produces vibration reduction in excess of 90% from baseline vibration levels. However for BVI alleviation flap deflections and power requirements are 3-4 times higher than those required for vibrations due to high-speed flight.
5. Developed improved vibration control laws in presence of limits on flap deflections, which result in actuator saturation and loss of vibration reduction effectiveness. Saturated flaps only reduces vibratory loads by an average of 30% while the baseline control input produces over a 90% reduction.
6. A new control procedure for limiting flap deflection authority was developed. In this approach the controller adjusts the control-weighting matrix automatically until flap deflections are within the prescribed limits. With a 4 degree limit on flap deflection, an 80% vibration reduction is achieved despite the practical limit imposed on the flap deflections.
7. Aeroelastic scaling laws were developed, which are particularly useful, when dealing with systems where actuation is provided by active materials.

IV. Publications

The research results have been presented and published at a large number of conferences and journals during this program. One of the conference papers submitted in 1996 received the best paper award from the Adaptive Structures and Material System committee of ASME. In addition to the large number of conference and symposium papers, some of which are reviewed, a number of journal articles have either been submitted or accepted by reputable journals. The following provides a list of research published in journal and conference papers during the conduct of this MURI

Journal Publications

Fotinich, Y. and Carman, G.P., "Modeling Polycrystalline Behavior of Piezoceramics", accepted to *Journal of Ferroelectrics*, Dec. 2001.

Salloux, K., Lim, J., Dunn, B., Chaplya, P., and Carman, G.P., "Rechargeable Lithium Batteries for Powering Piezoelectric Devices", *Journal of Intelligent Material Systems and Structures*, Vol. 11, No. 12, Dec 2000, pp. 930-936.

Chaplya, P. and Carman, G.P., "Dielectric and Piezoelectric Response of Lead Zirconate Titanate at High Electric and Mechanical Loads in Terms of Non-180 Domain Wall Motion", *Journal of Applied Physics*, Vol. 90, No. 10, November 2001, pp. 5278-5286.

Park, J., Keller, S., Carman, G.P., and Hahn, H.T., "Development of a Compact Displacement Accumulation Actuator Device for Both Large Force and Large Displacement", *Sensors and Actuators*, Vol. 90, 2001, pp. 191-202.

Friedmann, P.P., Carman, G., and Millott, T.A., "Magnetostrictively Actuated Control Flaps for Vibration Reduction in Helicopter Rotors - Design Considerations for Implementation", *Mathematical and Computer Modelling*, Vol. 33, 2001, pp. 1203-1217.

Chu, L., Chen, Q., and Carman, G.P., "Strength Prediction for Interlocking Microridges of the Mesoscale Actuator Device by Finite Element Analysis", *Journal for Microelectromechanical Systems*, Vol. 10, No. 2, 2001, pp. 310-315.

Park, J., Carman, G.P., and Hahn H.T., "Design and Testing of a Mesoscale Actuator Device", *Journal Intelligent Material Systems and Structures*, Vol. 11, Sept. 2000, pp. 671-680.

Chen, Q., Kim, C.J., Carman, G.P., "Investigating the Influence of Fabrication Process and Crystal Orientation on Shear Strength of Silicon Microcomponents", *Journal of Material Science*, Vol. 35, No. 21, March 2000, pp. 5465-5474.

Ho, K. and Carman, G.P., "Sputter Deposition of NiTi Thin Film SMA Using a Heated Target", *Journal of Thin Solid Films*, Vol. 370, 2001, pp. 18-29.

Fotinich, Y. and Carman, G.P., "Nonlinear Modeling of Polarization Switching in a Piezoceramic", *Journal of Applied Physics*, Vol. 88, No. 11, 2001, pp. 6715-6725.

- Keefe, A. and Carman, G.P., "Thermo-Mechanical Characterization of Shape Memory Alloy Torque Tube Actuators", *Smart Materials and Structures*, Vol. 9, 2000, pp. 665-672.
- Duenas, T. and Carman, G.P., "Large Magnetostrictive Response of Terfenol-D Resin Composites", *Journal of Applied Physics*, Vol. 87, No. 9, Dec. 1999, pp. 4696-4701.
- Mitrovic, M., Carman, G.P., and Straub, F., "Electro-Mechanical Characterization of Piezoelectric Stack Actuators", *International Journal of Solids and Structures*, Vol. 8, No. 224-25, 2001, pp. 4357-4374.
- Chen Q., Kim C.J., and Carman, G.P., "Mesoscale Actuator Device: Micro Interlocking Mechanism to Transfer Macro Load", *Sensors and Actuators*, Vol. 73, 1999, pp. 30-36.
- Chen, Q., Yao D., Kim, C.J., and Carman, G.P., "Development of Mesoscale Actuator Device with Micro Interlocking Mechanisms", *Journal of Intelligent Materials Systems and Structures*, Vol. 9, No. 6, June 1998, pp. 449-458.
- Park, S.B., Park S.S., Carman, G.P., and Hahn, H.T., "Measuring Strain Distribution During Mesoscopic Domain Reorientation in a Ferroelectric Material", Transactions of the ASME. *Journal of Engineering Materials and Technology*, Vol. 120, No.1, Jan. 1998, pp. 1-6.
- Wang, D., Fotinich, E., and Carman, G.P., "Influence of Temperature on the Electro-mechanical and Fatigue Behavior of Piezoelectric Ceramics", *Journal of Applied Physics*, Vol. 83, No. 10, May 1998, pp. 5342-5350.
- Park, S.B. and Carman, G.P., "Minimizing Stress Levels in Piezoelectric Media Containing Elliptical Voids", Transactions of the ASME. *Journal of Applied Mechanics*, Vol.64, No. 3, September 1997, pp. 466-70.
- Park, S.B. and Carman, G.P., "Tailoring the Properties for Piezoelectric Ceramics: Analytical", *Journal of Solids and Structures*, Vol. 34, No. 26, Sept. 1997, pp. 3385-3399.
- Yi T. and Kim, C.J., "Measurement of Mechanical Properties for MEMS Materials", *Measurement Science and Technology*, Vol. 10, No. 8, Aug. 1999, pp. 706-716.
- Yi, T., Li, L., and Kim, C.J., "Microscale Material Testing of Single Crystalline Silicon: Process Effects on Surface Morphology and Tensile Strength", *Sensors and Actuators*, Vol. 83, May 2000, pp. 172-178.
- Friedmann, P.P., "The Renaissance of Aeroelasticity and Its Future", *Journal of Aircraft*, Vol. 36, No. 1, January-February 1999, pp. 105-121.
- Myrtle, T.F., and Friedmann, P.P., "Application of a New Compressible Time Domain Aerodynamic Model to Vibration Reduction in Helicopters Using an Actively Controlled Flap", *Journal of the American Helicopter Society*, Vol. 46, No. 1, January 2001, pp. 32-43.

Friedmann, P.P., de Terlizzi, M., and Myrtle, T.F., "New Developments in Vibration Reduction with Actively Controlled Trailing Edge Flaps", *Mathematical and Computer Modeling*, Vol. 33, No. 10/11, April 2001, pp. 1055-1083.

Park, J., Tari, M.J., and Hahn, H.T., "Characterization of the Laminated Object Manufacturing (LOM) Process," *Rapid Prototyping Journal*, Vol. 6, 2000, pp. 36-50.

Conference and Symposium Publications

Chaplya, P.M. and Carman, G.P., "The Effect of Mechanical Prestress on Dielectric and Piezoelectric Response of PZT-5H at High Electric Fields", *Adaptive Structures and Material Systems*, Orlando, FL, Nov. 2000, pp. 327-334.

Mitrovic, M., Carman, G.P., and Straub, F., "Durability Properties of Piezoelectric Stack Actuators Under Combined Electro-Mechanical Loading", *Smart Structures and Materials 2000, Active Material Behavior and Mechanics*, SPIE Vol. 3992, pp. 217-232.

Fotinich, Y. and Carman, G.P., "Nonlinear Behavior of Polycrystalline Piezoceramics", *Smart Structures and Materials 2000, Active Material Behavior and Mechanics*, SPIE Vol. 3992, pp. 319-330.

Chen, Q., and Carman, G.P., "Microscale Tribology (Friction) Measurement and Influence of Crystal Orientation and Fabrication Process", (50 papers accepted out of 450 submitted), *MEMS 2000 Japan*.

Ho, K., Gill, J., and Carman, G.P., "Sputter Deposited NiTi Thin Film SMA for Active Flow Control", *10th International Conference on Adaptive Structures 1999*, pp. 197-208.

Chaplya, P. and Carman, G.P., "Crack Initiation Between Dissimilar Oriented Domains As A Possible Accelerated Fatigue Test", *ASME Adaptive Structures and Material Systems Symposium, AD-Vol 59*, Nashville, TN, Nov. 1999 pp. 105-111.

Mitrovic, M., Carman, G.P., Straub, F., "Electro-Mechanical Characterization of Piezoelectric Stack Actuators", *SPIE Smart Structures Conference 1999*, Vol. 3668, pp. 586-601.

Keefe, A., and Carman, G., "Thermo-Mechanical Characterization of Shape Memory Alloy Torque Tubes", *SPIE Smart Structures Conference 1999*, Vol. 3675, pp. 295-303.

Ho, K., Carman, G.P., and Jardine, P., "Sputter Deposition of NiTi Thin Film Exhibiting the SME at Room Temperature", *SPIE Smart Structures Conference, 1999*, Vol. 3675, pp. 252-267.

Chen, Q., Yao, D., Kim, C.J., and Carman, G.P., "Influence of Fabrication and Crystal Orientation on the Strength of Silicon Microridges", *ASME WAM 1998, Micro-Electro-Mechanical Systems (MEMS) 1998*, pp. 413-421.

Duenas T. and Carman, G.P., "Experimental Results for Magnetostrictive Composites", ASME 1998, Adaptive Structures and Material Systems, pp.63-73

Keefe, A, Carman, G.P., and Jardine, A.P., "Torsional Behavior of Shape Memory Alloys", Proceedings of the SPIE - The International Society for Optical Engineering, Smart Materials Technology, Vol. 3324, pp. 58-68.

Chapyla, P & Carman, G.P., "Relation of the Cracking Phenomena in Piezoelectrics to Domain Wall Motion", Proceedings of the SPIE - The International Society for Optical Engineering, Smart Materials Technology, Vol. 3324, pp. 154-161.

Chen, Q., Carman, G.P., and Kim CJ, "Frequency Response of an Inchworm Motor Fabricated with Micromachined Interlocking Surface Mesoscale Actuator Device (MAD)", Smart Structures and Integrated Systems, San Diego, Proceedings of the SPIE - The International Society for Optical Engineering, 1998, Vol.3329, Pt. 1-2, pp. 768-79.

Fotinich, Y. and Carman, G.P., "Modeling of Polarization Switching in Piezoceramics," Proceedings of the SPIE - The International Society for Optical Engineering, Mathematics and Control in Smart Structure, 1998, vol.3323:96-10

Wang, D, and Carman, G.P., "Combined Electrical and Mechanical Fatigue of Piezoelectric Ceramics Undergoing Polarization Reversals for Large Displacement", Proceedings of the SPIE - The International Society for Optical Engineering, Smart Structures and Integrated System, Vol. 3329, Pt.1-2, pp. 210-21.

Chen, Q., Yao,D., Kim, C.J., and Carman, G.P., "Mesoscale Actuator Device with Micro Interlocking Mechanism", Eleventh IEEE International Workshop on Micro Electro Mechanical Systems", January 25-29,1998, Heidelberg, Germany.

Wang, D., Alexander, H., Chen, Q., Carman, G.P., Kim, C.J., and Ho C., "Piezoelectrically Driven Meso-Scale Actuator Device for Aerodynamic Control", AIAA Adaptive Structure Forum, FL, April 1997, pp. 1738-1747.

Park, S.S., Carman, G.P., and Park, S.B., "Moire Interferometer Applied to Piezoceramics Containing a Simulated Void", Smart Structures and Materials 1997 Smart Materials Technology, San Diego, 1997, pp. 120-129.

Fotinich, Y. and Carman, G.P., "Modeling the Nonlinear Behavior of Piezoceramics with FEM", Smart Structures and Materials 1997, SPIE, San Diego.

Friedmann, P.P., Carman, G.P., and Millot, T.A., "Magnetostrictive Actuated Control Flaps for Vibration Reduction in Helicopter Rotors - Design Considerations for Implementations", 36th Israel Annual Conference on Aerospace Sciences, Feb. 21-22, 1996.

Park, S.B., and Carman, G.P., "Linear and Nonlinear Behavior of Piezoelectric Materials", SPIE Smart Structures Meeting, Mathematics and Control in Smart Structures, San Diego, Feb. 1996, pp. 366-378.

Park, S.B., Park S.S., Carman, G.P., and Hahn, H.T., "Polarization Switching for Ferroelectric Materials", ASME WAM 1996, AD-Vol. 52, Atlanta, GA, pp. 603-613.

Wang, D., and Carman, G.P., "Evaluating the Behavior of Piezoelectric Ceramics Subjected to Thermal Loads", Adaptive Materials Systems Symposium, ASME AMD-Vol. 206, pp. 47-57, 1995.

Wang, D., and Carman, G.P., "Development of an Innovative Meso-scale Actuator Device", Adaptive Material Systems and Symposium, ASME Winter Annual Meeting, San Francisco, CA, 1995.

Park, S.B., Fotinich, Y., and Carman, G.P., "Minimizing Stress Fields Near Defects in Piezoceramics", 6th Int. conf. On Adaptive Structures, 1995, pp. 87-102

Yi, T. and Kim, C.J., "Microscale Material Testing: Etchant Effect on the Tensile Strength", Proc. Int. Conf. Solid-State Sensors and Actuators (Transducers'99), Sendai, Japan, June 1999, pp. 518-521.

Yi, T. and Kim, C.J., "Tension Test with Single-Crystalline-Silicon Microspecimen," Proc. MEMS (MEMS-Vol. 1), ASME Int. Mechanical Engineering Congress and Exposition, Nashville, TN, Nov. 1999, pp. 81-86.

Li, L., Yi, T., and Kim, C.J., "Effect of Mask-to-Crystal Direction Misalignment on Fracture Strength of Silicon Microbeam", SEM (Society for Experimental Mechanics) IX International Congress, Orlando, FL, June 2000.

Myrtle, T. and Friedmann, P.P., "Compressible Unsteady Aerodynamics for Aeroelastic Analysis of Helicopter Blades with Trailing Edge Flaps and Its Implementation", Paper No. 60, Proceedings of 22nd European Rotorcraft Forum, Brighton, United Kingdom, September 17-19, 1996, pp. 60.1-60.13.

Myrtle, T.F. and Friedmann, P.P., "Unsteady Compressible Aerodynamics of a Flapped Airfoil with Application to Helicopter Vibration Reduction", AIAA Paper No. 97-1083, Proceedings of 38th AIAA/ASME/ASCE/AHS/ASC Structures, Structural Dynamics and Materials Conference, Kissimmee, FL, April 7-10, 1997, pp. 224-240.

Myrtle, T.F. and Friedmann, P.P., "New Comprehensive Time Domain Unsteady Aerodynamics for Flapped Airfoils and Its Application to Rotor Vibration Reduction Using Active Control", Proceedings of 53rd Annual Forum of the American Helicopter Society, Virginia Beach, VA, April 29-May 1, 1997, pp. 1215-1231

Friedmann, P.P., "The Renaissance of Aeroelasticity and Its Future", Keynote Lecture, Proceedings of the International Forum on Aeroelasticity and Structural Dynamics, Rome, Italy, June 17-20, 1997, Volume I, Plenary Lectures, pp. 19-49.

Friedmann, P.P., "The Promise of Adaptive Materials for Alleviating Aeroelastic Problems and Some Concerns", Proceedings of Innovation in Rotorcraft Technology, June 24-25, 1997, London, U. K., pp. 10.1-10.16, Published by the Royal Aeronautical Society.

Friedmann, P. P., "Rotary-Wing Aeroelastic Scaling and Its Application to Adaptive Materials Based Actuation", AIAA Paper No. 98-2098, Proceedings of 39th AIAA/ASME/ASCE/AHS/ASC Structures, Structural Dynamics and Materials Conference, Long Beach, CA, April 20-23, 1998

Myrtle, T. F. and Friedmann, P. P. "Vibration Reduction in Rotorcraft Using the Actively Controlled Trailing Edge Flap and Issues Related to Practical Implementation", Proceedings of the 54th Annual Forum of the American Helicopter Society, Washington, D.C., May 20-22, 1998.

de Terlizzi, M. and Friedmann, P.P., "Aeroelastic Response of Swept Tip Rotors Including the Effects of BVI", Proceedings of the 54th Annual Forum of the American Helicopter Society, Washington, D.C., May 20-22, 1998.

Friedmann, P.P., Myrtle, T.F., and de Terlizzi, M., "New Developments in Vibration Reduction with Actively Controlled Trailing Edge Flaps", Paper No. DY07, Proceedings of the 24th European Rotorcraft Forum, Marseilles, France, September 15-17, 1998, pp. DY07.1-DY07.21.

Friedmann, P. P., "Rotary-wing Aeroelastic Scaling and Its Application to Adaptive Materials Based Actuation", Paper No. DY08, Proceedings of the 24th European Rotorcraft Forum, Marseilles, France, September 15-17, 1998, pp. DY08.1-DY08.18.

Friedmann, P. P., "Rotary-wing Aeroelastic Scaling and Its Implication for Adaptive Materials Based Actuation", Paper No. 3668-07, Proceedings SPIE's 6th Annual International Symposium on Smart Structures and Materials, Conference 3668-Smart Structures and Integrated Systems, March 1-5, 1999, Newport Beach, CA.

DeTerlizzi, M. and Friedmann, P.P., "BVI Alleviation Using Active Control", AIAA Paper 99-1220, Proceedings of the 40th AIAA/ASME/ASCE/AHS/ ASC Structures, Structural Dynamics and Materials Conference, St. Louis, MO, April 12-15, 1999.

De Terlizzi, M. and Friedmann, P.P., "Active Control of BVI Induced Vibrations Using a Refined Aerodynamic Model and Experimental Correlation", Proceedings of 55th Annual Forum of the American Helicopter Society, Montreal, Canada, May 25-27, 1999, pp. 599-618.

Friedmann, P.P. and de Terlizzi, M., "Active Control of Vibrations Due to Blade Vortex Interaction (BVI)- Simulation and Experimental Correlation", Proceedings of 40th Israel Annual Conference on Aerospace Sciences, Paper 9.2, Tel-Aviv and Haifa, February 23-24, 2000.

Cribbs, R.C. and Friedmann, P.P., "Actuator Saturation in Actively Controlled Trailing Edge Flaps", Paper No. 28, Proceedings of the 26th European Rotorcraft Forum, Den Hague, The Netherlands, September 26-28, 2000, pp. 28.1-28.11.

Friedmann, P.P., "Rotary -Wing Aeroelasticity - Current Status and Future Trends", AIAA Paper 2001-0427, 39th AIAA Aerospace Sciences Meeting & Exhibit, Reno, NV, January 8-11, 2001, pp. 1-29 (Invited Keynote Lecture).

Friedmann, P.P., "Aeroelastic Scaling for Rotary-Wing Aircraft with Applications", AIAA Paper 2001-1534, Proceedings of the 42nd AIAA/ASME/ASCE/AHS/ASC Structures, Structural Dynamics and Materials Conference, Seattle, WA, April 16-19, 2001, pp. 1-15.

Cribbs, R.C. and Friedmann, P.P., "Actuator Saturation in Actively Controlled Trailing Edge Flaps", AIAA Paper 2001-1467, Proceedings of the 42nd AIAA/ASME/ASCE/AHS/ASC Structures, Structural Dynamics and Materials Conference, Seattle, WA, April 16-19, 2001, pp. 1-11.

Liu, W.P., Alexander, H. G., Ho, C.-M., "Separation Bubble Control for Gentle Stall on a Wortmann Airfoil" 19th ASME Wind Energy Symposium and 39th AIAA Aerospace Sciences Meeting and Exhibit, Reno, NV Jan 10-13 2000. AIAA Paper 2000-0069.

Salloux, K. and Dunn, B., "In-Situ Atomic Force Microscopy during Electrochemical Intercalation of Vanadium Oxide Xerogels", Electrochemical Society, Boston, MA, Nov. 1998.

Barrera, T.P. and Dunn, B., "Pulse Discharge of Lithium Gel-polymer Electrolyte Primary Cells", Electrochemical Society, Los Angeles, CA, May, 1996.

IV. AWARDS AND HONORS

The principal investigators participating on this program have received a number of awards and honors over the MURI program. These include national and international recognition. The following represents an abbreviated version of some of the awards given to our principal investigators during this MURI program.

- Chih-Ming Ho elected to membership in the National Academy of Engineering.
- Chih-Ming Ho Member of Academia Sinica
- Peretz Friedmann recipient of 1996 AIAA Structures, Structural Dynamics and Materials Award.
- Peretz P. Friedmann selected the SDM Lecturer at the 38th AIAA/ASME/ASCE/AHS/ACS SDM conference
- Tom Hahn recipient of Medal of Excellence in Composite Materials from University of Delaware Center for Composite Materials.
- Tom Hahn recipient of Ho-Am Prize in Engineering
- Bruce Dunn named fellow American Ceramics Society.
- Bruce Dunn won Materials Science Award for Outstanding Accomplishment in Metallurgy and Ceramics; Department of Energy (Office of Basic Energy Sciences)
- C.J. Kim recipient of National Science Foundation Career award.

- Greg Carman recipient of best paper award from Adaptive Structures and Material Systems ASME.
- Greg Carman recipient of Northrop-Grumman Young Investigator Award

V. SCIENTIFIC PERSONNEL SUPPORTED

The ARO MURI funding developed a large research infrastructure at UCLA. The research activities of six professors in the areas of Active Materials, Material Science, Mechanics, Rotorcraft Aeroelasticity, Experimental Fluid Mechanics, and MEMS were supported. More than 24 graduate students have received direct financial support on this grant with an additional 6 graduate students using the research infrastructure setup by the grant. In addition to graduate students, a number of undergraduate students participated on the program. Five postdoctoral scholars have been supported along with one technician. The following provides a list of support during the last two years.

Principal Investigators

Greg P. Carman
 Bruce Dunn
 Peretz Friedman
 Tom Hahn
 Chih-Ming Ho
 CJ Kim

Engineers

Scott Keller

Postdocs

Quanfang Chen
 Tom Barrera
 Robert Cribbs
 Seungbae Park
 Milan Mitrovic

PhD students who earned degree on program

Chaplya, Paul
 Park, Joon,
 Fotinich, Eugene
 Wang, Donny
 Kurt Salloux
 Taechung Yi
 Timothy Myrtle
 Marino deTerlizzi
 Hani Alexander

MS students who earned degree on program

Keefe, Andrew
Lung-His, Chu
Zheng, Rong
Johal, Raman,
Roberts, Mark
Park, Sung
Van-Way, Craig
Brandon, Eby
Stam, Mike
Wayne Liu
Eric Prophet
Jimmy Lim
Poyi Huang
Jinghui Zhu
Lu Li

VI. TECHNOLOGY TRANSFER

A number of industries have expressed strong interest in our research program. To satisfy this interest and promote technology transfer, we formed an industrial advisory board (IAB) containing over 15 organizations. The IAB has met for four consecutive years (1996, 1997, 1998, and 1999) at UCLA following the SPIE Smart Structures and Materials conference in San Diego, California. Many of the companies are also providing financial and in-kind support to the UCLA research effort. Therefore, based on this strong involvement our program is viewed as highly successful by the industrial community. At this meeting the industries are provided access to our data and many use the results that we have generated in designing/building actuation systems for their applications. For example, the piezoelectric stack characterization is routinely requested by these and other industries. The following list provides an indication of companies involved with UCLA and potential technology transfer.

- Northrop Grumman (\$140k in cash other in-kind support provided)
- Boeing (\$270k cash)
- McDonnell Douglas (\$50k in cash other in-kind support provided)
- Rockwell (over \$50k in-kind material)
- Sikorsky (Cooperative Research Agreement signed)
- Aeroflightmechanics Lab Ames Research Center (yearly meetings)
- Sandia National Lab
- Channel (over \$5k in-kind material)
- Xinetics (over \$8k in-kind material)
- Memry Co (over \$1k in-kind material)
- Etrema (over \$40k + in-kind material)
- Satcon (\$150k in cash support)
- MTS (\$75k in-kind equipment)
- Micron (\$5k in-kind support)
- Orbital Research (\$50k in cash)
- Lawrence Livermore National Lab (\$40k in cash)
- Piezokinetics/DARPA STTR (\$50k in cash)

- Structures and Materials/DARPA STTR (\$35k in cash)
- Burleigh/DARPA CHAP program (\$281k in cash)
- IBM (\$50k in-kind equipment)
- Lockheed
- Naval Research Lab
- others